

Conplast R*

Retarding water reducing admixture

Uses

- To improve the effectiveness of the water content of a concrete mix.
- To extend the setting time of concrete, extending working times and minimising delay problems.
- To extend the working life of semi-dry concrete screeds
- Particularly suitable for use in mixes having fly ash and also improve the working life of semi dry concrete mixes, specifically RCC (Roller Compacted Concrete) type of mixes.

Advantages

- Water reduction significantly improves compressive strengths at all ages and enhances durability through the production of low permeability concrete
- Controlled retardation extends working life and stiffening time for ease of construction
- Control of stiffening improves slip forming and assists in preventing the formation of cold joints in large pours
- Allows specified strength grades to be met at reduced cement content or increased workability
- Chloride free, safe for use in pre-stressed and reinforced concrete

Standards compliance

Conplast R complies with BS 5075 Part 1 and with ASTM C494 as Type B and Type D.

Description

Conplast R is a chloride free water reducing admixture based on selected hydroxycarboxylic materials. It is supplied as a brown solution which instantly disperses in water.

It is supplied as a Conplast R disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more. The initial hydration of the cement is also delayed, resulting in a delay in the setting time of the concrete with no adverse effect on subsequent stiffening and strength gain.

Technical Support

Fosroc provides a technical advisory service for on-site assistance and advice on admixture selection, evaluation trials and dispensing equipment. Technical data and guidance can be provided for admixtures and others products for use with fresh and hardened concrete.

Typical dosage

The optimum dosage of Conplast R to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. This allows the optimisation of admixture dosage and mix design and provides a complete assessment of the concrete mix. A starting point for such trials is to use a dosage within the normal typical range of 0.25 to 0.60 litres / 100 kg of cementitious material, including PFA, GGBFS or microsilica.

Use at other dosages

Dosages outside the typical range quoted above may be used if necessary and suitable to meet particular mix requirements, provided that adequate supervision is available. Compliance with requirements must be assessed through trial mixes. Fosroc shall be contacted for advice in these cases.

Properties

Appearance	: Clear Liquid
Specific gravity	: Typically 1.13 - 1.15 at 27°C
Chloride content	: Nil to BS:5075
Air entrainment	: Typically slightly less air will be entrained than in a normal concrete mix
Alkali content	: Na ₂ O equivalent /litre of admixture.

Application Instructions

Compatibility

Conplast R is compatible with other Fosroc admixtures used in the same concrete mix. All admixtures should be added to the concrete separately and must not be mixed

Conplast R*

together prior to addition. The resultant properties of concrete containing more than one admixture should be assessed by the trial mix to ensure that effects such as unwanted excessive retardation C494 as Type B and Type D. brown solution which instantly disperses in water effectively. Technical support cementitious material, including PFA, GGBFS or microsilica. Properties Typically 1. Typically slightly less air will normal concrete mix. Typically less than 55.0g do not occur.

Conplast R is suitable for use with all types of ordinary Portland cements and cement replacement materials such as PFA, GGBFS and silica fume. Further information on such usage is provided elsewhere on this datasheet.

Dispensing

The correct quantity of Conplast R should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Fosroc shall be contacted for advice regarding suitable equipment and its installation.

Effects of overdosing

An overdose of double the intended amount of Conplast R will result in a significant increase in retardation as compared to that normally obtained at the intended dosage. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased. The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used.

An overdose will tend to increase the plasticising effect of the admixture. As concrete is normally batched to a target workability, increased plasticising will allow an increased water reduction. This will have the effect of increasing ultimate strength and partially or fully offsetting the effect of any increased air entrainment. If no increase in water reduction is taken, and a significant rise in workability is allowed, the chance of segregation may be higher. Increased initial workability will tend to extend the working life of the concrete, which will delay finishing and stiffening times to some extent.

Over dosage may also lead to reduced mix cohesion and

may cause segregation and bleeding, particularly in high workability mixes. The degree of this effect will depend on the particular mix design and overdose level.

Curing

As with all structural concrete, good curing practice should be maintained, particularly in situations where an overdose has occurred. Water spray, wet hessian or a Concure spray applied curing membrane should be used.

Estimating

Packaging

Conplast R is available in 210 litre drums.

Storage

Conplast R has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then Fosroc shall be consulted.

Freezing point: Approximately -4°C .

Precautions

Health and safety instructions

Conplast R should not be swallowed or allowed to come into contact with skin and eyes. Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes it shall be rinsed immediately with plenty of water and medical advice sought immediately. If swallowed, medical attention shall be sought immediately. Vomiting should not be used.

Fire

Conplast R is water based and non-flammable.

Cleaning and disposal

Spillages of Conplast R should be absorbed onto sand, earth or vermiculite and transferred to suitable containers.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

Conplast R*

Example 1 : Laboratory testing for normal ready mixed concrete at 27 °C

Cement content 305kg/m³, gravel aggregates, all mixing carried out at equal workability

Mix	Dosage litres/100kg	Stiffening : 0.5N/mm ² BS5075 initial	Time to reach		W/C ratio	Compressive strength N/mm ²		
			3.5N/mm ² BS5075 Final -ASTMC408initial	27.6 N/mm ² - ASTMC403final		3D	7D	28 D
Control	-	4hr30	8hr00	7hr 30	0.68	20.5	28.0	37.5
Conplast R	0.28	6hr30	8hr00	10hr 00	0.62	24.5	35.0	46.0
Conplast R	0.42	8hr00	9hr15	11hr 30	0.58	27.5	37.5	47.5
Conplast R	0.56	10hr 00	11hr 15	13hr 30	0.58	27.5	39.0	49.0

Example 2 : Laboratory testing for normal ready-mixed concrete containing microsilica replacement

Gravel aggregate, mixes carried out with 100% OPC and with 5% microsilica replacement


Mix	OPC/MS kg/m ³	Dosage litres/100kg	W/C ratio	Slump mm	Setting time BS5075 Final	Compressive strength			
						1day	3day	7day	28day
Control	325	-	0.52	85	3hr 35	21.5	33.0	41.0	53.5
Conplast R	325	0.30	0.48	95	6hr 10	22.5	41.0	52.5	67.5
Control	310/15	-	0.63	85	3hr 30	22.0	36.0	43.0	80.5
Conplast R	310/15	0.30	0.49	90	6hr 05	23.0	42.0	50.0	74.5

Example 3: Laboratory testing for RCC(Roller compacted concrete) containing Fly ash as a supplementary Cementitious material at 20 C

40 MSA, Mixes carried out with 40 % OPC and 60 % Fly ash, replacement.

Mix	OPC/Fly Ash kg/m ³ wt of cement	Dosage % by	W/C	VeBe	I.S.T Time (ASTM C 403)	F.S.T	Compressive strength N/mm ²		
							3 day	7 day	28 days
Control	88/132	-	0.57	21	2 hrs 35	3 hrs 40	5.6	10	15
Conplast R	88/132	0.4	0.57	14	7 hrs 10	8 hrs 35	5.2	10.4	16.8
Conplast R	88/132	0.8	0.57	12	13 hrs 15	15 hrs 05	4.6	9.8	15.2
Conplast R	88/132	1.2	0.57	10	18 hrs 35	20 hrs 45	4.2	8.9	14.8
Conplast R	88/132	1.6	0.57	10	22 hrs 50	25 hrs 20	3.2	8.3	13.5
Conplast R	88/132	2.0	0.57	9	28 hrs 10	31 hrs 35	2.0	7.7	13.0

Conplast R*



* Denotes the trademark of Fosroc International Limited

† See separate datasheet



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Fosroc Singapore

30 Toh Guan Road
#07-07, ODC District Centre
Singapore 608840

telephone:
++ 65 6665 3828

fax:
++ 65 6899 1283

email:
Fosroc_Singapore@Fosroc.com