

**Technical Data Sheet**  
 Edition 2, 2005  
 Identification no.  
 02 04 01 04 001 0 000004  
 Version no. 0010  
**Sikadur® -330**

# Sikadur®-330

## 2-part epoxy impregnation resin

**Product Description** Sikadur®-330 is a two part, solvent free, thixotropic epoxy based impregnating resin / adhesive.

**Uses**

- Impregnation resin for SikaWrap® fabric reinforcement for the dry application method.
- Primer resin for the wet application system.
- Structural adhesive for bonding Sika® CarboDur® plates to even surfaces.

**Characteristics / Advantages**

- Easy mix and application by trowel and impregnation roller.
- Manufactured for manual saturation methods.
- Excellent application behaviour to vertical and overhead surfaces.
- Consistency can be chosen for application by brush or by trowel
- Good adhesion to many substrates.
- High mechanical properties.
- No separate primer required.
- Solvent free.

**Tests**

**Approval / Standards** Conform to the requirements of :

- SOCOTEC (France): Cashier des charges Sika® CarboDur, SikaWrap®
- Road an Bridges Research Institute (Poland): IBDiM No AT/2003-04-336

### Product Data

**Form**

**Appearance / Colours**

Resin part. A:	paste
Hardener part B:	paste
<i>Colour</i>	
Part A:	white
Part B:	grey
Part A+B mixed	light grey

**Packaging** Standard:  
5 kg (A+B) pre-dosed units

### Storage

**Storage Conditions / Shelf life** 24 months from date of production if stored properly in original unopened, sealed and undamaged packaging in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight.



Table of Contents

## Technical Data

**Chemical Base** Epoxy resin

**Density** Mixed Resin: 1.31 kg/l (at +23°C)

**Viscosity** Shear rate: 50 /s

Temperature	Viscosity
+10°C	~ 10'000 mPas
+23°C	~ 6'000 mPas
+35°C	~ 5'000 mPas

**Thermal Expansion Coefficient**  $45 \times 10^{-6}$  per °C (-10°C to +40°C)

**Thermal Stability** Heat Distortion Temperatures (HDT) (ASTM D648)

Curing	Temperature	HDT
7 days	+10°C	+36°C
7 days	+23°C	+47°C
7 days	+35°C	+53°C
7 days, +10°C plus 7 days, +23°C	-	+43°C

**Service Temperature** -40°C to +50°C

### Mechanical / Physical Properties

**Tensile Strengths** 30 N/mm<sup>2</sup> (7 days at +23°C) (DIN 53455)

**Bond Strengths** Concrete fracture on sandblasted substrate: > 1 day (EN 24624)

**E-Modulus**  
*Flexural*  
3800 N/mm<sup>2</sup> (7 days at +23°C) (DIN 53452)

*Tensile*  
4500 N/mm<sup>2</sup> (7 days at +23°C) (DIN 53455)

**Elongation at Break** 0.9% (7 days at +23°C) (DIN 53455)

### Resistance

**Chemical Resistance** The product is not suitable for chemical exposure.

**Thermal Resistance** Continuous exposure +50°C

## System Information

**System Structure** Substrate primer - Sikadur®-330  
Impregnating/laminating resin - Sikadur®-330  
Structural strengthening fabric - SikaWrap® type to suit requirements.

### Application Details

**Consumption** This will be dependant on the roughness of the substrate and the type of SikaWrap® fabric to be impregnated. See respective SikaWrap® fabric Product Data Sheet.

Guide: 0.7 – 1.5 kg/m<sup>2</sup>

**Substrate Quality**

The substrate must be sound and of sufficient tensile strength to provide a minimum pull off strength of 1.0 N/mm<sup>2</sup> or as per the requirements of the design specification.

The surface must be dry and free of all contaminants such as oil, grease, coatings and surface treatments etc.

The surface to be bonded must be level (max. deviation 2 mm per 0.3 m length), with steps and formwork marks not greater than 0.5 mm. High spots can be removed by abrasive blasting or grinding.

Wrapped corners must be rounded to a minimum radius of 20 mm (depending on the SikaWrap<sup>®</sup> fabric type) or as per the design specification. This can be achieved by grinding edges or by building up with Sikadur<sup>®</sup> mortars.

**Substrate Preparation**

Concrete and masonry substrates must be prepared mechanically using abrasive blast cleaning or grinding equipment, to remove cement laitance, loose and friable material to achieve a profiled open textured surface.

Timber substrates must be planed or sanded.

All dust, loose and friable material must be completely removed from all surfaces before application of the Sikadur<sup>®</sup> -330 preferably by brush and industrial vacuum cleaner. Weak concrete/masonry must be removed and surface defects such as honeycombed areas, blowholes and voids must be fully exposed.

Repairs to substrate, filling of blowholes/voids and surface levelling must be carried out using Sikadur<sup>®</sup> -41 or a mixture of Sikadur<sup>®</sup> -30 and Sikadur<sup>®</sup> -501 quartz sand (mix ratio 1 : 1 max parts by weight).

Bond tests must be carried out to ensure substrate preparation is adequate.

Inject cracks wider than 0.25 mm with Sikadur<sup>®</sup> -52 or either suitable Sikadur<sup>®</sup> injection resin.

**Application Conditions / Limitations**

<b>Substrate Temperature</b>	+10°C min. / +35°C max.
<b>Air Temperature</b>	+10°C min. / +35°C max.
<b>Substrate Humidity</b>	≤4% moisture content. Test method: Sika-Tramex meter
<b>Dew Point</b>	Beware of condensation! Ambient temperature during application must be at least 3°C above dew point.

**Application Instructions**

**Mixing** Part A : part B = 4 : 1 by weight

When using bulk material the exact mixing ratio must be safeguarded by accurately weighing and dosing each component.

**Mixing Time**



*Pre-batched units*

Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 600 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its pot life.

*Bulk packing, not pre-batched*

First, stir each part thoroughly. Add the parts in the correct proportions into a suitable mixing pail and stir correctly using an electric low speed mixer as above for pre-batched units.

**Application Method /  
Tools**



*Preparation:*

Prior to application confirm substrate moisture content, relative humidity and dew point.

Cut the specified SikaWrap<sup>®</sup> fabric to the desired dimensions.

*Resin Application*

Apply the SikaDur<sup>®</sup> -330 to the prepared substrate using a trowel, roller or brush.

*Fabric Placement and Laminating*

Place the SikaWrap<sup>®</sup> fabric in the required direction onto the SikaDur<sup>®</sup> -330. Carefully work the fabric into the resin with the Sika plastic impregnation roller parallel to the fiber direction until the resin is squeezed out between and through the fiber strands and distributed evenly over the whole fabric surface. Avoid excessive force when laminating to prevent folding or creasing of the SikaWrap<sup>®</sup> fabric.

*Additional Fabric Layers*

For additional layers of SikaWrap<sup>®</sup> fabric, apply SikaDur<sup>®</sup> -330 to previous applied layer wet on wet within 60 minutes (at +23°C) after application of the previous layer and repeat laminating procedure.

If it is not possible to apply within 60 minutes, a waiting time of at least 12 hours must be observed before application of next layer.

*Overlays*

If a cementitious overlay is to be applied over SikaWrap<sup>®</sup> fabric an additional Sikadur-330 resin layer must be applied over final layer at a max. 0.5 kg/m<sup>2</sup>. Broadcast with quartz sand while wet which will serve as a key for the overlay.

If a coloured coating is to be applied, the wet Sikadur<sup>®</sup>-330 surface can be smoothed with a brush.

*Overlaps*

*Fiber Direction*

- Overlapping of the SikaWrap<sup>®</sup> fabric must be at least 100 mm (depending on the SikaWrap<sup>®</sup> fabric type) or as specified in the strengthening design.

*Side by Side*

- Unidirectional fabrics: when placing several unidirectional SikaWrap<sup>®</sup> fabric side by side no overlapping is required unless specified in the strengthening design.

- Multi-directional fabrics: overlapping in the weft direction must be at least 100 mm (depending on the SikaWrap fabric type) or as specified in the strengthening design

**Cleaning of Tools**

Clean all equipment immediately with Sika<sup>®</sup> Colma Cleaner. Cured material can only be mechanically removed.

**Pot life (max. open time)****Pot life**

Temperature	Time
+10°C	90 minutes (5 kg)
+35°C	30 minutes (5 kg)

Pot life starts with the mixing of both parts (resin and hardener). At low ambient temperature pot life will be extended, at elevated temperatures this will be reduced. The higher the quantity of material mixed, the shorter the pot life. To achieve a longer pot life at high temperatures the mixed material may be divided into smaller units or both parts may be cooled before mixing.

**Open time**

Temperature	Time
+10°C	60 minutes
+35°C	30 minutes

**Waiting Time / Overcoatability**

To (pre-) cured resin:

Products	Substrate Temperature	Minimum	Maximum
Sikadur®-330	+10°C	24 hours	Cured resin older than 7 days has to be degreased with Sika® Colma Cleaner and gently grinded with a sand paper before coating.
Sikadur®-330	+23°C	12 hours	
	+35°C	6 hours	

Products	Substrate Temperature	Minimum	Maximum
Sikadur®-330	+10°C	5 days	Cured resin older than 7 days has to be degreased with Sika® Colma Cleaner and gently grinded with a sandpaper before coating.
Sikagard®-coloured coatings	+23°C	3 days	
	+35°C	1 day	

Times are approximate and will be affected by changing ambient conditions.

**Notes on Application / Limitations**

This product may only be used by experienced professionals.

The SikaDur® -330 must be protected from rain for at least 24 hours after application.

Ensure placement of fabric and laminating with roller takes place within open time. The SikaWrap® fabric must be coated with a cementitious overlay or coating for aesthetic and/or protective purposes. Selection will be dependent on exposure requirements. For basic UV protection use Sikagard® -550 W elastic, Sikagard® -ElastoColor-675W or Sikagard® -680S.

At low temperatures and / or high relative humidity, a tacky residue (blush) may form on the surface of the cured Sikadur-330 epoxy. If an additional layer of fabric, or a coating is to be applied onto the cured epoxy, this residue must first be removed to ensure adequate bond. The residue can be removed with water. In both cases, the surface must be wiped dry prior to application of the next layer or coating.

For application in cold or hot conditions, pre-condition material for 24 hours in temperature controlled storage facilities to improve mixing, application and pot life limits.

The number of additional fabric layers applied wet on wet must be closely controlled to avoid creeping, creasing or slippage of the fabric during curing of the Sikadur® -330. The number of layers will be dependent on the type of SikaWrap® fabric used and the ambient climate conditions.

**Applied product ready for use**

Temperature	Full cure
+10°C	7 days
+23°C	5 days
+35°C	2 days

All cure times are approximate and will be affected by changing ambient conditions.

**Notes**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**Health and Safety Information**

**Protective Measures**

To avoid rare allergic reactions, we recommend the use of protective gloves and goggles. Change soiled work clothes and wash hands before eating and after finishing work.

Local regulations as well as health and safety advice on packaging labels must be observed.

**Important Notes**

Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.

Mixed leftovers of Sikadur-330 may only be left to cure in metal containers and in quantities of max. 1 kg.

Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the safety data sheet.

**Legal Notes**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



**PT. Sika Indonesia**  
 Jl. Raya Cibinong- Bekasi km. 20  
 Limusnunggal- Cileungsi  
 BOGOR 16820 - Indonesia  
 Tel. +62 21 8230025  
 Fax +62 21 8230026  
 Website : [www.sika.co.id](http://www.sika.co.id)  
 e-mail: [sikacare@id.sika.com](mailto:sikacare@id.sika.com)

**Branches**  
 Surabaya :  
 Puri Niaga Blok G No. 29, Jl. Raya Rungkut Menanggal 11, Surabaya  
 Tel : 031-8690202 ; Fax : 031-8682123  
 Medan :  
 Jl. Pancing / Jl. Willem Iskandar No.75 & 75 A, Kec. Medan Tembung  
 Tel : 061- 6619500; Fax : (061) 6619400  
 Batam :  
 Jl. Laksamana Bintan, Komp. Bumi Riau Makmur Blok E No.3, Sungai Panas  
 Tel : (0778) 424928; Fax : (0778) 450189

